



AEROSPACE TAPES





Whether flame retardance, UV or moisture resistance, abrasion protection, or another application-specific performance feature, Polyken Engineered Tape Technologies provide the ultimate balance of performance attributes to meet challenging specification-driven applications for the aerospace industry.



PATCO engineers understand that every Aerospace application - from moisture barrier to surface protection - has inherent performance requirements that call for customized solutions. That is why for more than 50 years, PATCO has provided the Aerospace OEM and aftermarket industry with the world's most advanced portfolio of Performance Engineered Tapes.

| 03 | CARGO PIT SEALING TAPES |
|----|-----------------------------------|
| 04 | MOISTURE BARRIER TAPES |
| OS | CARPET TAPES |
| 06 | MOUNTING TAPES |
| 07 | FOIL & SPEED TAPES |
| 08 | INTERIOR SURFACE PROTECTION TAPES |
| 09 | EXTERIOR SURFACE PROTECTION TAPES |
| 10 | MEDIA BLAST & MASKING TAPES |
| 1 | CLOTH TAPES |
| 12 | PE FILM TAPES |
| 13 | ELECTRICAL TAPES |
| 14 | Specification Table |
| 15 | Shelf Life & Storage |
| 15 | Other Products |

Cargo Pit Sealing Tapes

Flame-retardant, high tensile strength, and excellent puncture and tear resistance are required for covering seams as well as patching and repairing panels in critical aircraft cargo compartments.

POLYKEN cargo compartment tapes offer these features and more including lightweight constructions that help reduce overall aircraft weight for fuel and cost savings.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Adhesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Weight oz/sy / g/sm | Operating Temp. ${}^{\circ}_{F}/{}^{\circ}_{C}$ | Colors |
|--|---|---|-----------------------|-----------------------------------|----------------------------------|------------------------|---|-------------------|
| Polyken 22 | 25FR Flame Retard | ant Duct Tape | | | | | | |
| PE Coated Cloth w/ Rubber Adhesive | Flame retardant. Durable, waterproof backing. High adhesion. Deca-BDE Free. | Non-passenger aircraft as a cargo seam tape. Douglas DMS 1968E; Fokker Fk05-006, Fk05-113, FAR 25.853(a)(1)(i); Lockheed LCP-86-1226-A | 12.0 0.305 | 40 4.38 | 29 50.79 | 10.0 339.1 | 40 - 200 4 - 93 | White Printed |
| Polyken 29 | 90FR Heavy-Duty (| Cargo Pit Tape | | | | | | |
| PE/Fiberglass Cloth w/ Rubber Adhesive | Flame retardant. Lightweight construction. Superior abrasion resistance. Resists lifting and curling. Removes clean. Deca-BDE Free. | Cargo hold floor panel seam sealing. Repair of cargo compartment liners. Covering pins and rivets. FAR 25,853(a); FAR 25.855(d); Airbus ABD0031, Para 7.3.2 & 7.4; Boeing 737-SL-25-115-B, 757-SL-25-085-B, 747-SL-25-195-B, 767-SL-25-112-B, 777-SL-25-037-B; Bombardier DSC 91-8-2 & 91-18-2A | 13.0 0.330 | 38 4.16 | 150 262.69 | 13.4 453.3 | 40 - 200 4 - 93 | White Printed |
| Polyken 29 | 96FR Lightweight C | Cargo Pit Tape | | | | | | |
| Fiberglass Cloth w/ Acrylic Adhesive LDPE Liner | Bromide-free and flame- retardant. Conformable to accommodate corners. Repositionable and clean removal. Lightweight construction saves cost. | Lightweight tape for cargo hold floor panel seam sealing. Repair of cargo compartment liners. Covering pins and rivets. FAR 25,853(a); FAR 25.855(d); Airbus ABD0031, Para 73.2 & 74; Boeing BMS5-146M, 737-SL-25- 115-B, 757-SL-25-085-B, 747-SL-25-195-B, 767-SL- 25-112-B, 777-SL-25-037-B | 7.0 0.178 | 45 4.92 | 134 234.67 | 6.8 210.0 | -40 - 275 -40 - 135 | White P or U/P |
| Polyken 29 | 97 Multi-Purpose C | argo Pit Tape (Unprinted) | | | | | | |
| Fiberglass Cloth w/ Rubber Adhesive LDPE Liner | Flame-retardant. High- tensile fiberglass backing. Superior abrasion and moisture resistance. Resist lifting and curling. High shear adhesive maintains seal under loads. Deca-BDE Free. | Mid-weight tape for cargo hold floor panel seam sealing. Repair of cargo compartment liners. Covering pins and rivets. FAR 25,853(a); FAR 25.855(d); Boeing 737-SL-25-115-B, 757-SL-25-085-B, 747-SL-25-195-B, 767-SL-25-112-B, 777-SL-25-037-B; Bombardier DSC 91-18-2A | 8.0 0.203 | 50 5.47 | 150 262.69 | 8.1 274.7 | 40 - 200 4 - 93 | White |

Moisture Barrier Tapes

PATCO moisture barrier tapes offer conformability, exceptional resistance to water, chemicals, solvents, abrasion, and puncture. Designed to provide a waterproof seal on aircraft floor boards, PATCO moisture barrier tapes are deployed in the entryway, lavatory, galley, and other areas where water and moisture can penetrate carpet or other flooring surfaces resulting in potential corrosion and damage to critical aircraft systems.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Adhesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Weight oz/sy / g/sm | Operating Temp. $^{ec{arphi}}_{ec{arphi}}/^{ec{arphi}}_{ec{arphi}}$ | Colors |
|---|---|--|-----------------------|-----------------------------------|----------------------------------|------------------------|---|--------|
| Patco 1800 | PVC Moisture Bar | rier Tape | | | | | | |
| PVC Film w/ Acrylic Adhesive Kraft Paper Liner | Economical moisture protection. Conformable. Compatible with most sealants. Forms a permanent bond. | Moisture barrier for interior aircraft sections exposed to moisture such as galleys, lavatories, and entry ways. FAR 25.853(a); Fokker FK05-159 & FK05-160; Bombardier 91-25-1, 91-25-2, 91-25-3, 91-25-3, 91-25-4, 91-25-5, 9-25-6 | 9.5 0.241 | 50 5.47 | 25 43.78 | 10.7 362.8 | -40 - 200 -40 - 93 | Black |
| Patco D910 | 0/D9100SW PU M | oisture Barrier Tape | | | | | | |
| Interior-grade PU Film w/ Urethane Adhesive Self wound or 94# Kraft Liner | Tough, elastic backing. Bonds directly over wet sealants. Easy to use at wide widths. | Moisture barrier for interior aircraft sections exposed to moisture such as galleys, lavatories, and entry ways. FAR 25.853a; Boeing BMS 8-346 Type I & II Class 1; Airbus AIMS 10-05-004 (ABS 5093), ABD0031 Para 7.3.2 & 7.4; Fokker FK05-193 | 9.0 0.229 | 50 5.47 | 70 122.59 | 8.6 291.6 | -65 - 300 -54 - 149 | Clear |
| Patco D918 | 0 PU Heavy-Duty | Moisture Barrier Tape | | | | | | |
| Interior-grade PU Film w/ Urethane Adhesive 94# Kraft Liner | Tough, elastic backing. Bonds directly over wet sealants. Extra thickness for stay-flat and dimensional stability. Easy and fast to apply. | Moisture barrier for interior aircraft sections exposed to moisture such as galleys, lavatories, and entry ways. FAR 25.853(a): Fokker FK05-193 | 14.0 0.356 | 45 4.92 | 100 175.00 | 13.05 442.47 | -65 - 300 -54 - 149 | Clear |
| Patco D920 | 00 PU Heavy-Duty | Outdoor Moisture Barrier Tape | е | | | | | |
| Exterior-grade PU Film w/ Acrylic Adhesive HDPE Liner | Tough, highly elastic film. Flame-retardant. Non- yellowing. | Moisture seal for floor joints in wet areas such as galleys, lavatories, and doorways. FAR 25.853(a); Fokker FK05-193 | 14.0 0.356 | 80 8.75 | 80 140.10 | 12.60 427.21 | -40 - 275 -40 - 135 | Clear |
| Patco 9425 | FR SealDry [™] Lightv | veight Moisture Barrier Tape | | | | | | |
| Interior-grade PU Film w/ Acrylic Adhesive HDPE Liner | Contains no plasticizers or PBDEs. Tough, durable backing. Lightweight material saves cost. Moderately aggressive adhesive for repositioning and clean removal. | Light-weight moisture barrier for interior aircraft sections exposed to moisture such as galleys, lavatories, and entry ways. FAR 25.853(a); Boeing BMS 8-346, Type 1 Class 3; Bombardier BAMS 535-007 Type VI | 6.0 0.152 | 28 3.06 | 34 59.54 | 5.0 169.53 | -10 - 250 -23 - 157 | Clear |

Carpet Tapes

POLYKEN double-coated carpet tapes provide exceptional bonding to hold carpet in place in aircraft cabin interiors and stairs. Carpet tape eliminates the need for mechanical fasteners that not only add weight, but can also introduce hazard to the aircraft. They can be used to secure carpeting at the time of manufacture, during maintenance and also be used for in-field repairs to eliminate tripping hazards and reduce aircraft down-time. POLYKEN carpet tapes install easily and remove cleanly from floor panels for fast, easy changeover.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Achesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Weight oz/sy / g/sm | Operating Temp. $^{arphi / ^{\sim}_{C}}$ | Colors |
|---|---|---|-----------------------|---|----------------------------------|------------------------|--|-------------------|
| Polyken 10 | 8FR Premium Carpe | et Tape | | | | | | |
| Cloth w/ FR Rubber Adhesive HDPE Liner | High strength flame retardant adhesive bonds well to surfaces. Repositionable. Clean removal. | Carpet installation in passenger areas for aircraft, automotive, or marine applications. Mounting and bonding for general machine and shop handling. FAR 25.853(a); Boeing BMS 5-133 Type II, Class 1 & 2, BAC5034-4 Sec. 5.1.a(1)(b); Bombardier DSC 91-8-1 & 91-8-2; Embraer MEP 06-048; Fokker FK05-121 & FK05-197; Lockheed LAC C-24-1257 | 15.0 0.381 | 60 6.56 | 55 96.32 | 13.0 472.9 | 40 - 200 4 - 93 | Natural, Black |
| Polyken 11 | 11FR Lightweight Car | rpet Tape | | | | | | |
| Lightweight PET Film w/ Differential Adhesive Kraft Liner | Ultra-lightweight formulation for improved fuel economy. High strength flame retardant adhesive bonds well to surfaces. Repositionable. Clean removal. | Carpet installation in passenger areas for aircraft, automotive, or marine applications. Multi-purpose mounting and bonding. Additional delivery option available: 1112FR with liner on low adhesion side. FAR 25.853(a): Boeing BMS 5-133 Type IV, Class 1; Airbus ABD0031, Para 7.2 & 7.4 | 3.9 0.099 | Floor/Air 42 4.60 Carpet/ Liner 126 13.80 | 27 152.6 | 4.5 152.6 | 20 - 180 -7 - 82 | Black/ Gray |
| Polyken 10 | 5C Multi-Purpose C | arpet Tape | | | | | | |
| Non-FR Cloth w/ Rubber Adhesive LDPE or Kraft Liner | Excellent adhesion particularly for rough surfaces. Clean removal. Easy-to-use release liner for smooth unwind. | Temporary carpet installation (non-FR). Multi- purpose mounting and bonding for general machine and shop handling. Boeing BAC5034-4 Sec. 5.1.a(1)(a) | 11.0 0.279 | 40 4.38 | 20 35.03 | 8.8 298.4 | 40 - 200 4 - 93 | Natural |



Mounting Tapes

POLYKEN double-coated film mounting tapes offer a thin, low-profile adhesive that bonds permanently to plastics, aluminum, steel, paper, vinyl and more to secure bonded details such as signs, placards, decals, and interior trim pieces throughout the aircraft. Also used for temporary hold-down uses, double-coated mounting tapes can secure parts and materials during milling and machining operations.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Adhesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Weight oz/sy/g/sm | Operating Temp. ${}^{arphi F/{}^{\circ} C}$ | Colors |
|---|---|--|-----------------------|---|----------------------------------|----------------------|---|--------|
| Polyken 30 | 6H High-Bond Mour | nting Tape | | | | | | |
| PET Film w/ Acrylic Adhesive Kraft Liner | Excellent adhesion. High shear strength and abrasion resistance. Chemical and moisture resistant. Permanent hold. | Securing signs, placards, decals, and interior trim pieces on aircraft. General purpose mounting and hanging. Boeing BMS 5-173 Type 1, Class 1, Grade A | 4.3 0.109 | Air 88 / 9.63 Liner 93 / 10.17 | 16 28.02 | 3.8 128.9 | 30 - 200 -1 - 93 | Clear |
| Polyken 12 | 26 Light-Weight Mou | inting Tape | | | | | | |
| PET Film w/ Acrylic Adhesive Kraft Liner | Thin and conformable. Well-suited to high temperature applications. High tack for quick grab to surfaces. | Temporary bonding for machining and milling of aircraft parts. Securing nameplates, faceplates, and decorative trim. | 3.8 0.097 | 25 2.74 | 6.0 10.51 | 3.0 101.7 | 0 - 395 -17 - 201 | Clear |
| Polyken 72 | 26 Light-Weight Mou | unting Tape (Red) | | | | | | |
| PET Film w/ Acrylic Adhesive Kraft Liner | Thin and conformable. Well-suited to high temperature applications. High tack for quick grab to surfaces. | Temporary bonding for machining and milling of aircraft parts. Securing nameplates, faceplates, and decorative trim. | 3.8 0.097 | 25 2.74 | 6.0 10.51 | 3.0 101.7 | 0 - 395 -17 - 201 | Red |

Foil & Speed Tapes

POLYKEN offers a variety of foil tapes designed for multiple maintenance and aircraft uses - from heat shielding, surface masking and protection during paint stripping, welding applications, autoclaving and composites, repair uses, to insulation sealing, and more. The POLYKEN assortment features several foil thicknesses to deliver conformability and strength as well as either rubber or acrylic adhesive options to suit the temperature requirements of unique and challenging applications.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Adhesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Elongation % | Operating Temp. $^{\circ}F/^{\circ}C$ |
|---|--|--|-----------------------|--------------------------------------|----------------------------------|-----------------|---------------------------------------|
| Polyken 3 | 45SW Self-Wound Spe | eed Tape | | | | | |
| 3 mil Aluminum Foil w/ Acrylic Adhesive | Excellent adhesion. Clean removal from most surfaces. High shear strength and abrasion resistance. Superior chemical and moisture resistance. | Aircraft sealing and masking applications to prevent crazing and hazing during point stripping. Moisture barrier in the production of military munitions and appliances. Anodizing, electroplating, and composites. FAR 25.853(a); SAE AMS-T-23397B; L-T-80B; Fokker Fk 05-011 | 5.0 0.127 | 68 7.44 | 26 45.53 | 3 | -40 - 350 -40 - 177 |
| Polyken 34 | 47 Linered Speed Tap | е | | | | | |
| 3 mil Aluminum Foil w/ Acrylic Adhesive Kraft Liner | Excellent adhesion. Clean removal adhesive. High shear strength and abrasion resistance. Superior chemical and moisture resistance. Available 26" width. | Aircraft sealing and masking applications to prevent crazing and hazing during paint stripping. Moisture barrier in the production of military munitions and appliances. Anodizing, electroplating, and composites. FAR 25.853(a); SAE AMS-T-23397B; L-T-80B; Fokker Fk 05-011 | 5.0 0.127 | 68 7.44 | 26 45.53 | 3 | -40 - 350 -40 - 177 |
| Polyken 33 | 32 Utility Grade Foil T | ape | | | | | |
| 1.5 mil Aluminum Foil w/ Synthetic Rubber Adhesive Kraft Liner | Exceptional quick-stick. Conformable foil backing. Easy to use and install. Mold and mildew resistant. | Insulation seaming and patching. General repair. UL 723 Classified | 3.2 0.081 | 75 8.21 | 11 19.26 | N/A | 40 - 200 4 - 93 |
| Polyken 33 | 30X High Temperature | e Foil Tape (260 °F) | | | | | |
| 1.75 mil Aluminum Foil w/ Acrylic Adhesive Kraft Liner | Exceptional performance in all temperature environments. Conformable foil backing. Easy to use. High Tack. Mold and mildew resistant. | Sealing and masking in extreme heat, extreme cold, and indoor/outdoor conditions in aerospace applications. General repairs. UL 723 Classified; FAR 25.853(a) | 3.5 0.089 | 55 6.02 | 14 24.52 | N/A | -35 - 260 -37 - 126 |
| Polyken 33 | 35FT High Temperatu | re Foil (500 °F) | _ | | | | |
| 1.75 mil Aluminum Foil w/ Acrylic Adhesive Kraft Liner | Exceptional performance in all temperature environments. Conformable foil backing. Easy to use. High Tack. Mold and mildew resistant. | Sealing and masking in extreme heat, extreme cold, and indoor/outdoor conditions in aerospace applications. General repairs. UL 723 Classified; FAR 25.853(a) | 3.5 0.089 | 55 6.02 | 14 24.52 | N/A | -50 - 500 -65 - 460 |

Interior Surface Protection

Featuring clean removal adhesive systems, PATCO interior surface protection tapes are deployed during maintenance operations to protect a variety of aircraft surfaces from scratches, puncture, and exposure to moisture or chemicals. Designed to remove cleanly after the maintenance operations are complete, interior surface protection tapes can be used on control panel surfaces, wood and coated surfaces, fabrics and leather, plastics, metals, and more.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Adhesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Elongation % | Operating Temp. ${}^{arphi F/^{\circ}_{\mathcal{C}}}$ | Colors |
|---|--|---|-----------------------|-----------------------------------|----------------------------------|-----------------|---|----------------------------|
| Patco 5565 | FR PE General Surfac | e Protection Tape | | | | | | |
| LDPE Film w/ Acrylic Adhesive | Thick, highly conformable. Abrasion, moisture, and solvent- resistant. Clean removal from most surfaces. Easy to apply. Excellent all-temperature performance. | Aircraft general surface protection applications on various interior materials during maintenance and repair operations. FAR 25.853(a) | 5.5 0.140 | 12 1.31 | 12 21.02 | 500 | -40 - 190 -40 - 88 | Clear, Trans. Orange |
| Patco 8450 | PU Heavy-Duty Surfa | ice Protection Tape | | | | , | | |
| Interior-grade PU Film w/ Acrylic Adhesive 94# Kraft Liner | Tough, durable, abrasion-resistant film. Excellent aging properties. Solvent-resistant. Excellent conformability. | Heavy-duty surface protection on most metals and plastics. Squeak and rattle protection. Noise and vibration damping. Moisture barrier. | 9.5 0.241 | 75 8.21 | 40 70.05 | 700 | -40 - 250 -40 - 121 | Black |
| Patco 3910 | R PP Interior Surface P | Protection Tape | | | | | | |
| Embossed OPP Film w/ Rubber Adhesive | Conformable and heat-resistant. Does not lift during molding or shaping. Removes cleanly from most surfaces. Smooth, easy unwind. | Aircraft general surface protection applications for control panels, corners, panels, and signs that are subjected to possible damage during maintenance. | 4.1 0.104 | 17 1.86 | 14 24.52 | 700 | -40 - 325 -40 - 162 | Clear, Tinted Red |

Exterior Surface Protection

PATCO offers high performance tapes for protecting the exterior surfaces of aircraft. Applications include high visibility sealing and protecting critical static ports, direct protective mask during paint or cleaning operations, preservation and sealing during transport or storage, and leading edge protection to prevent chips and damage that can reduce aircraft efficiency. Designed for use outdoors, exterior surface protection tapes hold up to the elements during both short and long-term exposure uses.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Adhesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Elongation % | Operating Temp. %7/°C | Colors |
|---|---|--|-----------------------|-----------------------------------|----------------------------------|-----------------|--------------------------|------------------------------|
| Patco 5030 | Static Port Protection 1 | -ape | | | | | | |
| PE Film w/ Acrylic Adhesive | High visibility colors. Conformable. Excellent moisture barrier properties. High adhesion. Excellent high-low temperature performance. | High visibility static port protection. Temporary indoor/outdoor surface protection. Color coding and parts marking. General purpose sealing. | 5.5 0.140 | 50 5.47 | 11 19.26 | 400 | -40 - 190 -40 - 88 | Gloss Yellow, Orange, Red |
| Patco 5410 | PE Long-Term Outdoor | Protection Tape | | | | | | |
| UV-Stable LDPE Film w/ Rubber Adhesive | UV and weather-resistant. Excellent low temperature adhesion. Chemical and abrasion resistant. | Long-term preservation, sealing, and splicing applications. Direct protective mask on aircraft. Used in conjunction with outdoor shrink film for extended outdoor storage. | 9.0 0.229 | 25 2,74 | 17 29.77 | 600 | -40 - 200 -40 - 93 | White |
| Patco 8300 | PU Leading Edge Prote | ection Tape | | | | | | |
| Exterior-grade PU Film w/ Acrylic Adhesive 94# Kraft Liner | Clear, non-yellowing film backing. Excellent long-term aging. Will not lift, stain, or dry-out. Superior conformability and ease-of-use. | Exterior surface protection film for aircraft leading and trailing edges. Protects aluminum skin from foreign object damage and rain erosion. Fokker FK05-193 | 14.5 0.368 | 110 12.03 | 80 140.10 | 500 | -40 - 275 -40 - 135 | Clear |





Masking Tapes

Whether masking fine color separations, bulk masking for power washing or paint line applications, media blast masking protection, or protecting composites during manufacture, POLYKEN & PATCO offer engineered masking tape solutions providing the right balance of conformability, high temperature bonding, moisture and solvent resistance, and clean removal every time.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Adhesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Elongation % | Operating Temp. °F/°C | Colors |
|---|--|---|-----------------------|-----------------------------------|----------------------------------|-----------------|--------------------------|-------------------|
| Polyken 2 | 53 Media Blast Protection | n Tape | | | | | | |
| PE Coated Cloth w/ Rubber Adhesive | Extremely tough and durable backing withstands media blast exposure. High bond rubber adhesive holds strong to smooth or rough surfaces. | Temporary surface protection for sheet metal, aluminum, and other materials during sand blast or other media blast operations. Heavy duty bundling, sealing, and patching. | 12 0.330 | 95 10.39 | 50 87.56 | N/A | 40 - 200 4 - 93 | Silver, Black |
| Patco 179 | High Temp PVC Fineline | Masking Tape | | | | | | |
| PVC Film w/ Rubber Adhesive | Conformable to handle compound curves and details. Non-glare finish. Solvent-resistant. High temperature performance. Clean removal from most substrates. | Fineline masking on plastic fascia, trim, and finished metals during paint line and power wash. Short-term outdoor masking (<72 hrs). Electroplating and metal anodizing. | 5.5 0.140 | 15 1.64 | 15 26.27 | 100 | 40 - 280 4 - 138 | Blue (Matte) |
| Patco 1676 | 6 High Temp PVC Fineline | e Masking Tape | | | | | | |
| PVC Film w/ Rubber Adhesive | Conformable to handle compound curves and details. Strong tack and adhesion. Solvent-resistant. High temperature performance. Clean removal from most substrates. | OEM and aftermarket fineline masking. Paint line and power wash masking. Aircraft and clean room paint masking. | 5.5 0.140 | 24 2.63 | 16 28.02 | 110 | 40 - 280 4 - 138 | Light Blue |
| Patco 1776 | 6 High Temp PVC Fineline | Masking Tape | | | | | | |
| PVC Film w/ Rubber Adhesive | Extreme high temperature performance. Tough and conformable. Moisture and solvent-resistant. Repositionable. Clean removal from most substrates. Low stretch film. | OEM and aftermarket fineline masking. Paint line and power wash masking. | 5.5 0.140 | 22 2.41 | 17 29.77 | 190 | 40 - 325 4 - 162 | Yellow (Matte) |
| Patco 330 | 5 High Temp PP Fineline | Masking Tape | | | | | | |
| Embossed OPP Film w/ Urethane Adhesive | Translucent for easy application. Tough and conformable - doesn't wrinkle on curves and corners. Moisture and solvent-resistant. Repositionable. Clean removal from most substrates. | OEM and aftermarket fineline masking. Masking color separations on plastic, aluminum, steel, and fiberglass. Suitable for bake cycles of up to 280 °F for 45 minutes. | 5.0 0.127 | 30 3.28 | 13 22.77 | 700 | -40 - 250 -40 - 121 | Green |
| Polyken 7 | 81 PET Composite Protec | tion Tape | | | | | | |
| PET Film w/ Silicone Adhesive | Tough polyester film backing. Excellent adhesion to silicone-coated materials. Excellent shear strength and adhesion. Resists high temperatures and offers excellent chemical resistance. Self wound construction. | Mask and protect surfaces during anodizing and chemical milling. Composite moulding applications. | 2.8 0.071 | 35 3.83 | 25 43.78 | 130 | 0 - 395 -18 - 202 | Blue, Red |

Cloth Tapes

POLYKEN is a pioneer in the development of high performance cloth tapes for repair, bundling, color coding and marking, hanging and sealing PE sheeting, duct sealing, and more. POLYKEN multipurpose duct tapes, military-grade duct tapes, and matte-finish clean removal gaffer tapes perform in a wide range of aircraft maintenance facility uses.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Adhesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Operating Temp. %7/°C | Colors |
|---|--|---|-----------------------|-----------------------------------|----------------------------------|--------------------------|--|
| Polyken 20 | 3 Multi-Purpose Duct | Таре | | | | | |
| PE Coated Cloth w/ Rubber Adhesive | Good balance of adhesion, tensile, and tack. Excellent tear. Stiff adhesive offers clean removability from most surfaces. | Bundling, packaging, seaming, and general repairs. Color coding. | 9.0 0.229 | 85 9.30 | 27 47.28 | 40 - 200 4 - 93 | Silver, Black, Red, Blue, Green, Olive Drab, Brown, White, Yellow |
| Polyken 23 | 1 Premium Military Gro | ade Duct Tape | | | | | |
| PE Coated Cloth w/ Rubber Adhesive | Durable, waterproof backing. Extra high adhesion for permanent bonds. Crisp, straight tear. | Premium grade duct tape for packaging, sealing, and waterproofing. Meets ASTM D-5486 Type IV, Class 1; Douglas DPM 871-3 | 12.0 0.305 | 95 10.39 | 50 87.56 | 40 - 200 4 - 93 | Olive Drab, Black |
| Polyken 22 | 2 Premium Duct Tape | | | | | | |
| PE Coated Cloth w/ Rubber Adhesive | Durable, waterproof backing. Extra high adhesion for permanent bonds. Crisp, straight tear. | Premium grade duct tape for packaging, sealing, and waterproofing. | 12.0 0.305 | 90 9.85 | 36 63.05 | 40 - 200 4 - 93 | Olive Drab, Silver |
| Polyken 51 | O Premium Gaffer Tape | 9 | | | | | |
| Matte-Finish Coated Cloth w/ Natural Rubber Adhesive | Durable, matte-finish, printable backing. High adhesion and high shear. Clean removal from most surfaces. 12+ colors available. | Indoor/Outdoor wire hold-down. Color coding. Marking hazards. Parts identification. | 11.5 0.292 | 50 5.47 | 42 73.55 | 40 - 200 4 - 93 | Neon Yellow, Neon Pink, Neon Orange, Neon Green, Black, White, Gray, Beige, Burgundy, Navy Blue, Red, Green, Yellow, Brown, Tan, Teal, Olive Drab, Royal Blue, Purple |
| Polyken 51 | 2 Multi-Purpose Gaffer | Tape | | | | | |
| Matte-Finish Coated Cloth w/ Synthetic Rubber Adhesive | Durable, matte-finish, printable backing. High adhesion and high shear. Clean removal from most surfaces. 12+ colors available. | Indoor/Outdoor wire hold-down. Color coding. Marking hazards. Parts identification. | 12.0 0.305 | 66 7.22 | 40 70.05 | 40 - 200 4 - 93 | Black, White, Gray, Beige, Red, Brown, Navy Blue, Neon Orange, Neon Pink, Yellow |

PE Film Tapes

POLYKEN offers an exceptional range of polyethylene film tapes for indoor and outdoor uses such as hanging, sealing, seaming, patching, and repairing polyethylene sheeting and tarps. PE film tapes are ideal for temporary attachment of work orders, protective materials, labels, or placards, and can also be used to hang and seal sheeting materials to create temporary containment areas during cleaning and maintenance operations.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Adhesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Elongation % | Operating Temp. ${}^{q_{\mathcal{F}}/{}^{\eta_{\mathcal{C}}}}$ | Colors |
|---|--|---|-----------------------|-----------------------------------|----------------------------------|-----------------|--|-------------------------|
| Polyken 7 | 59 Heavy-Duty PE Filr | n Tape | | | | | | |
| PE Film w/ Synthetic Rubber Adhesive | Conformable. Thick and durable. Strong bond to poly sheeting. Excellent shear strength. | Heavy-duty polyethylene splicing and hanging. Creating temporary enclosure and containment areas. Dissimilar metal separation. | 9.0 0.229 | 85 9.30 | 30 52.54 | 65 | 40 - 200 4 - 93 | Clear, Red, White |
| Polyken 7 | 67UV Multi-Purpose O | outdoor PE Film Tape | | | | | | |
| PE Film w/ Synthetic Rubber Adhesive | UV resistant for up to 28 days of exposure. Removes clean from most surfaces. Excellent adhesion and tack. | Outdoor seaming, sealing, and hanging of poly sheeting. Creating temporary enclosure and containment areas. Dissimilar metal separation. Temporary outdoor surface protection. | 7.0 0.178 | 75 8.21 | 25 43.78 | 85 | 20 - 200 -7 - 93 | Red, White |
| Polyken 7 | 69UV Heavy-Duty Ou | tdoor PE Film Tape | | | | | | |
| PE Film w/ Synthetic Rubber Adhesive | UV resistant for up to 28 days of exposure. Removes clean from most surfaces. Excellent adhesion and tack. Strong, heavy-duty backing resists abrasion and the elements. | Outdoor seaming, sealing, and hanging of poly sheeting. Creating temporary enclosure and containment areas. Dissimilar metal separation. Temporary outdoor surface protection. | 9.0 0.229 | 85 9.30 | 32 56.04 | 70 | 20 - 200 -7 - 93 | Red, White |



Electrical Tapes

Utilizing our adhesive engineering experience for the automotive industry, POLYKEN offers a number of products uniquely suited for sealing, wrapping, splicing, and protecting electrical wires and harnesses used in the aerospace industry.



| Product Construction | Features | Applications/ Specifications | Thickness mil / mm | Adhesion to Steel oz/in / N/cm | Tensile Strength lb/in / N/cm | Operating Temp. %/°C | Colors |
|---|--|--|-----------------------|-----------------------------------|----------------------------------|-------------------------|--|
| Patco 1800 | Heavy-Duty Electrical | Таре | | | | | |
| PVC Film w/ Acrylic Adhesive Kraft Liner | Economical moisture protection. Conformable. Compatible with most sealants. Forms a permanent bond. | Heavy-duty electrical wrapping and splicing. High and low temperature applications. FAR 25.853(a) | 9.5 0.241 | 50 5.47 | 25 43.78 | -40 - 200 -40 - 93 | Black |
| Polyken 82 | 3 Premium Electrical To | ipe | | | | | |
| PE Film w/ Rubber Adhesive | Superior extreme weather performance including sub-zero conditions. Provides maximum electrical insulation properties. Solvent and moisture resistant. | Electrical and maintenance applications where PVC materials are not permitted. Wrapping and waterproofing wire harnesses. UL 510 Classified; Douglas DPM 881 | 9.5 0.241 | 31 3.39 | 17 29.77 | -40 - 180 -40 - 82 | Black |
| Berry 777/E | 317 General Purpose Ele | ectrical Tape | | | | | |
| PVC Film w/ Rubber Adhesive | Excellent stretch and conformability. Good adhesion. 600V/wrap dielectric strength. | General Purpose wrapping and splicing for electrical wires. Color coding. UL 510 Classified | 7.0 0.178 | 25 2.74 | 20 35.02 | 40 - 180 4 - 82 | Black (777) Blue, Green, White, Red (B17) |
| Stretch & S | eal Self-Fusing Silicone | Sealing Tape | | | | | |
| Self-Fusing Silicone Film Cellophane Liner | High temperature resistance. Bonds well even in wet conditions. Excellent abrasion resistance and dielectric strength. Leaves no residue. | Wrapping applications including electrical, light-duty pipe wrapping, plumbing and waterproofing. Excellent for temporary bundling and clamping. Wrap tool handles to form an instant grip. Also available FR. | 20.0 0.508 | N/A | 800 psi | -60 - 500 -51 - 260 | Black, Clear, White, Blue |

UL 510 Classified; A-A-59163 Type I and II

Specification Table

| SPECIFIER | SPECIFICATION NO. | PRODUCT NO. |
|--------------|------------------------------------|---|
| Airbus | AIMS 10-05-004A (ABS 5093) | Patco D9100, D9100SW |
| | ABD0031, Paragraphs 7.3.2 | Polyken 290FR, 296FR, 108FR, 1111; Patco D9100, D9100SW |
| | ABD0031, Paragraphs 7.4 | Polyken 290FR, 296FR, 1111; Patco D9100, D9100SW |
| | BMS 5-133 Type II, Class 1 & 2 | Polyken 108FR (Natural - Class 1; Black - Class 2) |
| | BMS 5-133 Type IV, Class 1 | Polyken 1111 |
| | BAC5034-4 Sec 5.1.a(1)(a) | Polyken 105C |
| | BAC5034-4 Sec 5.1.a(1)(b) | Polyken 108FR |
| | BMS 5-146 | Polyken 296FR |
| | BMS 8-346 Type I & II, Class 1 | Patco D9100, D9100SW |
| Boeing | BMS 8-346 Type I, Class 3 | Patco 9425FR |
| 3 | BMS 5-173 Type I, Class 1, Grade A | Polyken 36H |
| | 737-SL-25-115-B | Polyken 290FR, 297, 296FR |
| | 737-SL-25-085-B | Polyken 290FR, 297, 296FR |
| | 747-SL-25-195-B | Polyken 290FR, 297, 296FR |
| | 767-SL-25-112B | Polyken 290FR, 297, 296FR |
| | 777-SL-25-037-B | Polyken 290FR, 297, 296FR |
| | DSC 91-8-1 | Polyken 108FR |
| | DSC 91-8-2 | Polyken 108FR, 290FR |
| Bombardier/ | DSC 91-8-2A | Polyken 290FR |
| deHavilland | DSC 91-25-2, -3, -4, -5, -6 | Patco 1800 |
| | BAMS 535-007 Type VI | Patco 9425FR |
| | DMS 1968E | Polyken 225FR |
| | DPM 871-2 | Polyken 827 |
| Douglas / | DPM 871-3 | Polyken 827 & 231 |
| Boeing | DPM 877-1 | Polyken 827 |
| | DPM 881 | Polyken 823 |
| Embraer | MEP 06-048 | Polyken 108FR |
| FAA | FAR 25.853(a) | Polyken 290FR, 297, 296FR, 108FR, 225FR, 345SW, 347, 330X; Patco 5565FR, 1800, D9100, D9100SW, D9180, D9200, 9425FR |
| ., . | FAR 25.855(d) | Polyken 290FR, 294FR, 297, 296FR |
| | FK05-006, FK05-113 | Polyken 225FR |
| | FK05-011 | Polyken 345SW |
| Fokker | FK05-121, Fk05-197 | Polyken 108FR |
| | FK05-159 & FK05-160 | Patco 1800FR |
| | FK05-193 | Patco 8300, D9100, D9180, D9200 |
| | LCP-86-1226-A | Polyken 225FR |
| Lockheed | LAC C-24-1257 | Polyken 108FR |
| | A-A-59163 Type I & II | Nashua Stretch & Seal |
| | ASTM D-5486 Type IV Class 1 | Polyken 231 |
| Military | PPP-T-60D | Polyken 231 |
| 3 | L-T-80B | Polyken 345SW |
| | SAE AMS-T-23397B | Polyken 345SW |
| Underwriters | UL 510 | Berry B17, 777; Polyken 823; Nashua Stretch & Seal |
| Laboratories | UL 723 | Polyken 330X, 332 |
| | | |

Shelf Life, Storage, and More

*From date of manufacture. †From date of shipment.

| PRODUCT TYPE | PRODUCT NUMBERS | SHELF LIFE |
|---|--|---------------------|
| Cargo Pit Tapes | 290FR, 296FR, 297, 225FR | 2 years* |
| Carpet & Mounting Tapes | 108FR, 105C, 126, 726, 36H | 2 years* |
| Lightweight Carpet Tapes | 1111FR | 3 years* |
| Moisture Barrier & Electrical Tapes | 1800 | 1 year ⁺ |
| Moisture Barrier & Surface Protection Tapes | 8300, D9100, D9180, D9200, 9425FR | 2 years* |
| Surface Protection & Masking | 179, 1676, 1776, 3305, 5410, 5565FR, 3910R, 8450 | 1 year⁺ |
| Speed Tape | 345SW, 347 | 2 years* |
| PE Film Tapes | 759*, 767UV*, 769UV*, 823*, 5030 ⁺ | 2 years |
| Duct & Foil Tapes | 203, 222, 231, 253, 330X, 332, 335FT | 3 years* |
| Gaffer Tapes | 510, 512 | 1 year* |
| Electrical Tapes | 777, Stretch & Seal® | 1 year* |
| Electrical Tapes | B17 | 5 years* |

Recommended Storage

To ensure best possible shelf life, products should be stored

- in the original dry carton
- off of the floor
- · in a well-ventilated area
- in temperatures conditions from 60° 80 °F and relative humidity of 40 60%.

More from Berry Global...



DuraWipe™ general purpose industrial wipes are engineered from proprietary, triple-layer Spinlace® construction. These super-absorbent wipes are strong enough for the greasiest and grimiest of surfaces, yet soft enough to be used to clean hands and face. DuraWipe is available in a variety of sizes and colors.

VeraClean™ high-performance, low-linting critical cleaning wipes are ultra-soft and engineered to remove remaining residue, dirt particles, and fingerprints not necessarily visible to the eye. VeraClean is an ideal solution for automotive and aerospace manufacturing and aftermarket finishing touches.



Visit chicopee.com or email the Chicopee customer care team at specialty@berryglobal.com to learn more.

Military-Grade Flexible Packaging

Berry Global is a leader in laminated materials for use in packaging and protection applications. Designed for maximum strength, excellent durability, and long-term barrier protection, Berry's flexible packaging structures meet rigid military and government standards. Berry Global has the flexible packaging solution to meet your application needs!

Contact Berry Global customer care at 1-800-343-7875 today!



Specification List

| PECIFIER | SPECIFICATION NO. | PRODUCT NO. |
|--------------|------------------------------------|---|
| Airbus | AIMS 10-05-004A (ABS 5093) | Patco D9100, D9100SW |
| | ABD0031, Paragraphs 7.3.2 | Polyken 290FR, 296FR, 108FR, 1111; Patco D9100, D9100SW |
| | ABD0031, Paragraphs 7.4 | Polyken 290FR, 296FR, 1111; Patco D9100, D9100SW |
| Boeing | BMS 5-133 Type II, Class 1 & 2 | Polyken 108FR (Natural - Class 1; Black - Class 2) |
| | BMS 5-133 Type IV, Class 1 | Polyken 1111 |
| | BAC5034-4 Sec 5.1.a(1)(a) | Polyken 105C |
| | BAC5034-4 Sec 5.1.a(1)(b) | Polyken 108FR |
| | BMS 5-146 | Polyken 296FR |
| | BMS 8-346 Type I & II, Class 1 | Patco D9100, D9100SW |
| | BMS 8-346 Type I, Class 3 | Patco 9425FR |
| | BMS 5-173 Type I, Class 1, Grade A | Polyken 36H |
| | 737-SL-25-115-B | Polyken 290FR, 297, 296FR |
| | 737-SL-25-085-B | Polyken 290FR, 297, 296FR |
| | 747-SL-25-195-B | Polyken 290FR, 297, 296FR |
| | 767-SL-25-112-B | Polyken 290FR, 297, 296FR |
| | 777-SL-25-037-B | Polyken 290FR, 297, 296FR |
| | DSC 91-8-1 | Polyken 108FR |
| | DSC 91-8-2 | Polyken 108FR, 290FR |
| Bombardier/ | DSC 91-8-2A | Polyken 290FR |
| deHavilland | DSC 91-25-2, -3, -4, -5, -6 | Patco 1800 |
| | BAMS 535-007 Type VI | Patco 9425FR |
| | DMS 1968E | Polyken 225FR |
| 5 | DPM 871-2 | Polyken 827 |
| Douglas / | DPM 871-3 | Polyken 827 & 231 |
| Boeing | DPM 877-1 | Polyken 827 |
| | DPM 881 | Polyken 823 |
| Embraer | MEP 06-048 | Polyken 108FR |
| FAA | FAR 25.853(a) | Polyken 290FR, 297, 296FR, 108FR, 225FR, 345SW, 347, 330X; Patco 5565FR, 180 D9100, D9100SW, D9180, D9200, 9425FR |
| | FAR 25.855(d) | Polyken 290FR, 294FR, 297, 296FR |
| | FK05-006, FK05-113 | Polyken 225FR |
| | FK05-011 | Polyken 345SW |
| Fokker | FK05-121, Fk05-197 | Polyken 108FR |
| | FK05-159 & FK05-160 | Patco 1800FR |
| | FK05-193 | Patco 8300, D9100, D9180, D9200 |
| | LCP-86-1226-A | Polyken 225FR |
| Lockheed | LAC C-24-1257 | Polyken 108FR |
| Military | A-A-59163 Type I & II | Nashua Stretch & Seal |
| | ASTM D-5486 Type IV Class 1 | Polyken 231 |
| | PPP-T-60D | Polyken 231 |
| | L-T-80B | Polyken 345SW |
| | SAE AMS-T-23397B | Polyken 345SW |
| | | • |
| Underwriters | UL 510 | Berry B17, 777; Polyken 823; Nashua Stretch & Seal |